The system NE 12 – for car-accessible areas on subterranean garages and parking decks NE 12 – The Car-Accessible Solution shows an excellent drainage performance and a high crush resistance. On basis of the values it is suitable for any application whether for parking decks on subterranean garages, access roads to neighbouring buildings or emergency access roads. 6 fürs Grün GmbH • Kanalstraße 2 • D-66130 Saarbrücken • Phone +49 681 - 960 21 46-0

Fax +49 681 - 960 21 46-26 • www.6-f-g.de • info@6-f-g.de

Drainage: NE 12 VF with geotextile and sliding foil 5 Separation, sliding and protection layer: TGL 550, GRK 5 6 Sliding layer: Construction foil PE-LD 0.2 mm

Base layer: Crushed stones (0/32), application height 12 - 15 cm

1 Top layer: Concrete paving stones 8 - 10 cm

Bedding: Chippings (0/4), application height 3 cm

2

3



Our Green Roof System NE 12 - The Car-Accessible Solution



- Flat Roofing Road Construction
- Garden Lighting
- Natural Ponds
- Artificial Turf
- Green Roofs



Drainage NE 12 VF with Geotextile and Foil

The drainage NE 12 VF is made of dimpled PE-HD membrane with a laminated filter layer on top and a sliding foil underneath. Due to a crush resistance of up to 1160 kN/m² it is eminent suitable as drainage and protective layer under car and lorry accessible areas. Depending on the set-up of the layers, an impact sound reduction of up to 33 dB can be achieved.

The drainage NE 12 VF with filter layer and sliding foil is harmless to drinking water, chemically neutral, root resistant, rot-proof and resistant to mould and bacteria.

Application

- as drainage under vehicle accessible areas

- for roofs with a pitch of $\ge 0^{\circ}$

Data



Subject		Unit	NE 12 VF
Raw material membrane			PE-HD
Raw material geotextile			PP
Weight membrane Weight geotextile Weight foil		g/m²	1000 136
			100
Total weight			1240
Colour membrane			black
Colour geotextile			silver grey
Height of dimples		mm	10
Quantity of dimples		pro m ²	3368
Drainage capacity on 20 kPa load (according DIN EN ISO 12958, rigid/soft)	i = 1.00	l/ms	3.48
	i = 0.01		0.33
	i = 0.02		0.45
	i = 0.05		0.71
Opening size geotextile (according to EN ISO 11058)		10 ³ m/s	50
Crush resistance (according EN ISO 25619-2)		kN/m²	1160 (116 t/m²)
Temperature resistance		°C	-40 up to + 80
Impact sound reduction		db	up to 33

Dimensions

Subject	Unit	NE 12 VF
Length	m	12.5
Width	m	2
m² / roll	m²	25
Weight / roll	kg	31

* All values are average values. Technical changes remain reserving